



## Uniguide II

Uniguide II is a premium quality oil specially developed to provide optimum lubrication of saw guides and saw blades in sawmills. It is particularly recommended for the lubrication of arbor bearings and saw guide systems that utilize "thin kerf" technology in cutting lumber.

Uniguide II is formulated to provide wear protection, tackiness, enhanced metal-wetting ability and protection against rust and corrosion. Oiliness and tackiness agents provide a strong oil film that reduces friction and resists sling-off during operation, resulting in extended saw guide life and reduced water usage for cooling. An extreme-pressure additive provides extra protection against saw guide wear.

Uniguide II homogenizes with water to form fine droplets to provide effective saw guide lubrication. It has excellent filterability and does not contain any chlorine or heavy metal compounds.

### **Applications**

- Saw guides and blades
- Arbor bearings
- Saw system ways and gears

Uniguide II is recommended for use in saw guide systems from all leading manufacturers, including:

- Coe Newnes/McGehee
- Salem
- USNR (Schurman, Ukiah)

### **Features/Benefits**

- Good metal-wetting ability
- Homogenizes in fine droplets in the presence of water
- Extreme-pressure properties for wear protection
- Resists sling-off
- Excellent filterability
- Protects against rust and corrosion
- Does not contain chlorine or heavy metals

**Premium  
Saw Guide Oil**

### **CONTACT INFORMATION**

**Phillips66  
Lubricants.com**

U.S. Customer  
Service:  
**1-800-368-7128**

Technical Hotline:  
**1-877-445-9198**

International  
Customer Service:  
**1-832-765-2500**

E-mail address:  
**lubricants@  
p66.com**



## Uniguide II

### Typical Properties

ISO Grade	32	46	100	150
Specific Gravity @ 60°F	0.861	0.871	0.875	0.880
Density, lbs/gal @ 60°F	7.17	7.25	7.29	7.32
Color, ASTM D1500	1.0	1.0	2.0	2.5
Flash Point (COC), °C (°F)	216 (420)	225 (437)	268 (514)	282 (540)
Pour Point, °C (°F)	-24 (-11)	-24 (-11)	-29 (-20)	-18 (0)
Viscosity,				
cSt @ 40°C	32.0	46.0	100	150
cSt @ 100°C	5.6	7.1	12.4	16.0
SUS @ 100°F	165	237	518	783
SUS @ 210°F	45.0	50.0	69.2	83.8
Viscosity Index	114	113	117	111
Foam Test, ASTM D892	Pass	Pass	Pass	Pass
Rust Test, ASTM D665 A	Pass	Pass	Pass	Pass

### Health and Safety Information

For recommendations on safe handling and use of this product, please refer to the Material Safety Data Sheet via <http://w3apps.phillips66.com/NetMSDS>.

Typical properties are average values only and do not constitute a specification. Minor variations that do not affect product performance are to be expected during normal manufacture, and at different blending locations. Product formulations are subject to change without notification.

© 2012 Phillips 66 Company, Phillips 66, 76, Conoco, Liquid Titanium and their respective logos and products are trademarks of Phillips 66 Company in the U.S.A. and other countries.